

A.C.N. 000 038 782

THOMS "SOFTA-FLASH" PUREZINC FLASHING

Zinc Flashing is manufactured from commercially pure alloy (99.95% minimum purity). It is compatible with ZINCALUME® and COLORBOND® coated steel roofing and walling.

Zinc Flashing is:

- Easily worked
- Malleable
- Easily soldered
- Stain resistant
- Non rusting
- Extremely durable

DIFFERENCE

To ensure trouble free installation:

- Always use the correct grade of Zinc.
- Use clips instead of nails to secure Zinc in position and allow for natural expansion.
- Allow Zinc to move freely.
- Use "killed spirits" as a soldering flux.
- Use 50/50 tin/lead solder.
- Use the soldering iron slightly cooler than for galvanised iron.
- Wash off residue flux with clean water after soldering.
- Don't solder copper to Zinc.
- Dry store Zinc until use.
- Don't use copper or ungalvanised iron in contact with Zinc or allow rainwater from these metals to flow onto zinc
- Don't use in acid conditions.
- Don't leave multiple sheets in weather.
- Don't leave coils of Zinc in weather.

Soft Zinc is designed for flashing use only and is not to be used for downpipes, eaves and box gutters. Special grades of Zinc are available for a variety of purposes.

"Softa-Flash"™ is produced to Australian Standard AS2904-1986, Damp-Proof Courses and Flashings.

Hard Zinc sheets and coils are sometimes used as flashing when soft zinc is unsuitable. Ensure the correct material is obtained by detailing the end use when ordering.

Hard Zinc is produced to Australian Standards AS2179/ 2180 - 1986 Metal Rainwater goods - specification, selection and installation.



STANDARD ROLL LENGTH 6 metre Thickness 0.7mm (nominal)

Width	Weight
110mm	3.2kg
150mm	4.3kg
230mm	6.7kg
300mm	8.7kg
380mm	11.0kg
460mm	13.3kg
580mm	16.8kg

THOMAS THOMS Pty. Limited

A.C.N. 000 038 782

6 ENTERPRISE STREET, WULKURAKA INDUSTRIAL ESTATE, IPSWICH QLD. 4305 PHONE: (07) 3281 0666 FAX: (07) 3282 7366

16 JUMAL PLACE, SMITHFIELD, NSW 2164 PO BOX 2141 SMITHFIELD, NSW 2164 PHONE: (02) 9604 8600 FAX: (02) 9604 8066

SUPPLIED BY:

THOMAS THOMS PTY. LIMITED - ESTABLISHED 1881

The description herein of the suggested uses of these products are in general terms only. No warranty is given or implied as to performance or suitability in any particular application and qualified advice should always be obtained. Neither the manufacturer or supplier shall be liable for any loss or damage arising out of inappropriate use.